



Adore





anthracite 67



army 14



aubergine 74



beige 05



blossom 166



blush 92



clay 84



coffee 81




cognac 28



copper 126



darkgrey 68



dolphin 180

Please note: colours may vary according to your screen settings.



ecru 102



forest 162



gold 132



hazel 96




hunter 156



indigo 90



laÛe 211



linen 110




liver 10



moss 59



natural 01



niagara 158

Please note: colours may vary according to your screen settings.



oyster 175




pale 200



petrol 56



sand 03



steel 149







tobacco 111



winered 39



wood 108



Please note: colours may vary according to your screen settings.

Adore - Article passport

Adore is a piece dyed kniGed velvet with a printed slub-effect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	kniged velvet
ApplicaGons	sofa's, beds, chairs with fiGed and loose fiGing upholstery
ComposiGon faceside	100%PES
ComposiGon backside	100%PES
Bonding	woven
StaGsGc code	60053700
Dyeing method	piece dyed
Available colours	32
Packaging	boxes

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	88.000		min. 20.000	min. 40.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	dark colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigareGe test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulaGons: 1988 No. 1324. Schedule 4 part 1 IgniGon source 0: cigareGe	CTL		passed				

Processingspecifications

Minimum workable width in cenGmeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 580							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	691	583	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	71,7	61,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,5	2,0	max. 5	max. 4	A/A
DelaminaGon	DIN 53530:1981-02	CTL	Newton	20,2	20,5	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		cerGified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	0,0	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp aHer washing.
 - Please note that during washing the damp- and dirt prevented treatment will disappear faster.
 - Dirt and damp prevenGon treatment applied.

