



Facet





Facet

This post-consumer woolen upholstery fabric is suitable for all types of upholstery. The yarns of Facet are made from post-consumer recycled woolen textiles and virgin polyamide.

The recycled yarns are carded from regenerated woolen products. Carding is a specific way of processing yarns. Due to an environmental friendly production process, used woolen clothing, fabrics & knits get a second life.

The result is a yarn and eventually a fabric like Facet, with a particular characteristic that distinguishes it from other virgin woolen yarns. The entire production and finishing process is done by an Italian textile specialist, known for this type of production for more than a century.

During use, a certain hairiness may appear, this has no further influence on the durability of this type of woolen fabrics. Due to the production process, each batch is unique and colour variations may occur.

Due to its composition FACET passes the BS5852 cigarette (part 0) & match (part 1) test and also the EN1021 cigarette (part 1) & match (part 2) test.

Facet has a light melange aspect and is available in a wide and trendy colour line from stock.

***Textafoamoriginals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 70%WO 25%PA 5%OF
/ backside n/a
/ flatweave

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67 (fr)



aqua 143 (fr)



army 14 (fr)



ashgrey 40 (fr)



aubergine 74 (fr)



azure 144 (fr)



beige 1037 (fr)



blossom 166 (fr)



blue 45 (fr)



darkbrown 18 (fr)



dolphin 180 (fr)



fire 139 (fr)

Please note: colours may vary according to your screen settings.



fuchsia 77 (fr)



indigo 90 (fr)




kiezel 7 (fr)



lightblue 41 (fr)



lightgrey 1000 (fr)



maize 22 (fr)



mandarin 129 (fr)



middengrijs 1001 (fr)



mint 50 (fr)



natural 01 (fr)



navy 1007 (fr)



nightshade 178 (fr)

Please note: colours may vary according to your screen settings.



oceanblue 147 (fr)



olive 53 (fr)



orange 2012/b (fr)



petrol 56 (fr)



pink 73 (fr)



pistachio 52 (fr)



prune 76 (fr)



purple 78 (fr)



red 2011 (fr)



rust 29 (fr)



shitake 124 (fr)



taupe 1008 (fr)

Please note: colours may vary according to your screen settings.



terra 31 (fr)



violet 72 (fr)



yellow 24 (fr)



zwart 1003 (fr)



Please note: colours may vary according to your screen settings.

Facet - Article passport

Woolly fabric with a soft grip, made from recycled material.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	70%WO 25%PA 5%OF
Composition backside	n/a
Bonding / Coating	n/a
Statistic code	51113080
Dyeing method	yarn dyed
Available colours	40
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	3-4		min. 3-4	min. 4	C
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette		Centexbel	passed				
	DIN EN ISO 1021-2:2014. Source: smouldering cigarette		Centexbel	passed				
	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 1: match flame equivalent		Centexbel	passed				
Ignitability (match test)	DIN EN ISO 1021-2:2014. Source: match flame equivalent		Centexbel	passed				

Processingspecifications

Minimum workable width in centimeters	± 145
Roll length in meters	± 50
Material weight in grams per linear meter	± 600

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	455	348	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	40,5	35,2	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,7	2,7	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl