




LEAF




ivory 101



ashgrey 40




stone 181



steel 149



taupe 12



brown 15




grey 65




lava 165




espresso 123



niagara 158



indigo 90



darkblue 48




eucalyptus 193




forest 162



mustard 06



scarlet 141



winered 39



hazel 96

Leaf - Article passport

Aluxurychenillebouclé yarn has been woven in the weft-direction. This gives this chunky and trendy new article a great hand feel.

Available from stock in a wider range of contemporary and commercial colours.

Product characteristics

Product group	chenille flat weave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Statistic Code	54075200
Coating	SBR
Dyeing method	yarn dyed
Available colours	18



Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09	
				DRY	WET	DGM	DGM+		
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	C	
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B	
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5	CTL	grade	light colours	5	min. 4	min. 5	B	
				middle colours	5	min. 4	min. 5	B	
				dark colours	5	min. 4	min. 5	B	
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11	CTL	grade	light colours	5	5	dry: 4, wet: 3	Dry: min. 4, wet: 3-4	A/A
				middle colours	4-5	4-5	dry: 4, wet: 3	Dry: min. 4, wet: 3-4	A/A
				dark colours	4-5	4-5	dry: 4, wet: 3	Dry: min. 4, wet: 3-4	A/A
Ignitability	BS5852 part 1 (1979) from The Furniture and Furnishings (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 0: cigarette	CTL		passed					

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 770							
Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	2.666	781	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	255,3	223,5	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	4,5	3,5	max. 5	max. 4	B/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Dimensional change for washing 30 degrees Celsius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	± 0,0	± 0,0	n/a	n/a	A/A
		We recommend to immediately place the cover back to the piece of furniture slightly damp after washing.						

Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle The
Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl