

















Member

This textile is made from 100% sustainable material and offers the best value for money, fitting every style all year round. Member is a 100% RPET woven fabric and is part of the www.wovenbottles.com collection.

A textile which has an elegant structure, with a rather soft handfeel, both the face side and the backing are made from plastic bottles. For more information on this sustainable production process, please visit our website www.fabraa.com.

Member has been woven on an air jet loom and has a trendy and wide colourline, suitable for all kinds of upholstery. Washable at 30 degrees Celsius (machine).

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

Fabraa Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-qualty, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

Composition

/ faceside 100%RPET / backside 100%RPET / flatweave

Suitable for



Please note: colours may vary according to your screen settings.



Member - Article passport

A 100% sustainable article with an elegant structure and rather soft handfeel.

Available from stock in a wide range of contemporary and commercial colours.

| Product characteristics | | | | | |
|-------------------------|---------------------------------------------------------------|--|--|--|--|
| Productgroup | flatweave | | | | |
| Applications | sofa's, beds, chairs with fitted and loose fitting upholstery | | | | |
| Composition faceside | 100%RPET | | | | |
| Composition backside | 100%RPET | | | | |
| Bonding | non-woven | | | | |
| Statistic code | 54075200 | | | | |

piece dyed

transparent plastic

18

| Durability s | pecifications |
|--------------|---------------|
|--------------|---------------|

Dyeing method

Available colours

Packaging

| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RALGZ430/4:2019-01 | | Norm DIN EN 14 465:2006-09 | |
|-------------------------------------|--------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------|------------|--------|-------------------------|-----------------------|-------------------------------|-----|
| | | | | Dry | Wet | DGM | DGM+ | | |
| Abrasion resistance - yarn breakage | | DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03 | CTL | cycles | 55.000 | | min. 12.000 | min. 16.000 | А |
| Pilling | | DIN EN ISO 12945-2:2000-11. 2000 cycles | CTL | grade | 4-5 | | min. 3-4 | min. 4 | А |
| Colour fastness to light | | DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5 | | | | | | | |
| | | light colours | CTL grade 4-5 | | | | min. 4 | min.5 | B-C |
| | middle colours | CTL | grade | 4-5 | | min. 4 | min.5 | B-C | |
| | | dark colours CTL grade 4 | | 4 | min. 4 | min.5 | С | | |
| Colour fastness to rubbing | | DIN EN ISO 105-X12:2016-11 | | | | | | | |
| | light colours | CTL | grade | 4-5 | 4-5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A | |
| | | | CTL | grade | 5 | 4-5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A |
| | | dark colours | CTL | grade | 4-5 | 4-5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A |
| gnitability (cigarette test) | | BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette | СТL | | pas | sed | | | |

Processingspecifications

| 0.1 | | | | |
|-------------------------------------------|-------|--|--|--|
| Minimum workable width in centimeters | ± 143 | | | |
| Roll length in meters | ± 40 | | | |
| Material weight in grams per linear meter | ± 450 | | | |
| | | | | |

| Material weight in grams per linear meter | ± 450 | | | | | | | |
|-------------------------------------------|-------------------------------------------|-------------------------|--------|------------|------|-------------------------|----------|-------------------------------|
| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RALGZ430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
| | | | | Warp | Weft | DGM | DGM+ | |
| Tensile strength | DIN EN ISO 13934-1:2013-08 | CTL | Newton | 770 | 489 | min. 350 | min. 400 | A/B |
| Tear growth resistance | DIN EN ISO 13937-3:2000-06 | CTL | Newton | 95,2 | 89,6 | min. 25 | min. 30 | A/A |
| Resistance to seam slippage | DIN EN ISO 13936-2:2004-07. Load 180 N | CTL | mm | 3,5 | 4,5 | max. 5 | max. 4 | A/B |
| Delamination | DIN 53530:1981-02 | CTL | Newton | 34,2 | 26,2 | n/a | n/a | n/a |
| Chemical substances | REACH | Centexbel | | pas | ssed | | | |
| | Oeko-Tex, product class II | Centexbel | | certified | | 1 | | |

Cleaning specifications

| 3-0-3 | | | | | | | | |
|----------------------------------------------------------------|---------------------------------------------------------------------------------|-------------------------|------|------------|------|-------------------------|------|-------------------------------|
| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RALGZ430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
| | | | | Warp | Weft | DGM | DGM+ | |
| Dimensional change for washing 30 degrees celcius / air drying | DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08 | CTL | % | 0,0 | 0,0 | n/a | n/a | A/A |























