

MIAMI



lightgrey 60



beige 05



ecru 102



zinc 167



natural 01




mustard 06



darkgrey 68



taupe 12




pesto 194



graphite 66




cacao 83



teal 198



burgundy 34



blush 92



indigo 90

Miami - Article passport


Anice, elegant and soft quality with voluminous grip.

Available from stock in a wider range of contemporary and commercial colours.

Product characteristics

Product group	chenille flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	70% PES 30% VI
Statistic Code	58013600
Coating	needle punch
Dyeing method	piecedyed
Available colours	15

Durability specifications






Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ 430/4:2016-01		Norm DIN EN 14465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	85.000		>8.000	>16.000	B
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	4		min.3-4	min.4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	5		min.4	min.5	B
	middle colours	CTL	grade	5		min.4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry:4, wet:3	dry:min 4, wet:3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry:4, wet:3	dry:min 4, wet:3-4	A/A
Colour fastness to rubbing	dark colours	CTL	grade	4-5	4	dry:4, wet:3	dry:min 4, wet:3-4	A/A
	Ignitability (cigarette test)	 BS5852 part 1 (1979) from The Furniture and Furnishings (Fire) (Safety) Regulations: 1988 No.1324, Schedule 4 part 1, Ignition source 0: cigarette	CTL		passed			

Processing specifications





Minimum workable width in centimeters	± 138							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 616							
Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ 430/4:2016-01		Norm DIN EN 14465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	861	446	min.350	min.400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	716	716	min.25	min.30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	2,3	2,3	max.5	max.4	A/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ 430/4:2016-01		Norm DIN EN 14465:2006-09
				WARP	WEFT	DGM	DGM+	
Dimensional change for washing 30 degrees Celsius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	- 0,8	- 1,6	n/a	n/a	A/A

We recommend to immediately place the cover back to the piece of furniture slightly damp after washing. Please note that washing has a negative effect on the damp- and dirt prevention treatment; by washing the treatment will disappear faster. Dirt and Damp prevention treatment applied



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl