



Rate





Rate

Fabricsthat offer the best value for money and suit everystyle all year round.
With Rate we developed a slightly rough constructed fabric with a light bicolour aspect.
Laminated with a non-woven backing, Ratefeels extra soft and voluminous.

Rate consists of a polyester yarn, woven on an air jet loom. Piece dyed and treated to be moisture and dirt repellent. Washable at 30 degrees (machine wash)*.

* Pleasenote that washing has a negative effect on the damp and dirt prevented treatment, by washing the treatment will disappear faster.

Composition

- / Faceside 100%PES
- / Backside 100%PES
- / Polyesterflatweave

Suitable for

Sofa's, beds, chairs with fitted and loose fitting upholstery

Rate - Article passport

Fabric with a light multi-coloured aspect and a soft and full hand feel.

Available from stock in a wider range of contemporary and commercial colours.

Product characteristics

Product group	polyester flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Composition backside	100% PES
Statistic Code	54075200
Bonding	non-woven
Dyeing method	piecedyed
Available colours	19

Durability specifications


Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	> 100.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min. 5	C
	middle colours	CTL	grade	4		min. 4	min. 5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	dark colours	CTL	grade	3-4	3	dry: 4, wet: 3	dry: min 4, wet: 3-4	C/B
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishings (Fire) (Safety) Regulations: 1988 No. 1324 Schedule 4 part 1. Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 143							
Roll length in meters	± 45							
Material weight in grams per linear meter	± 522							
Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1519	631	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	141,8	50,5	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180N	CTL	mm	2,0	2,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	34,7	19,3	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Dimensional change for washing 30 degrees Celsius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	- 0,8	0,0	n/a	n/a	A/A


 We recommend to immediately place the cover back to the piece of furniture slightly damp after washing. Please note that washing has a negative effect on the damp- and dirt prevented treatment; by washing the treatment will disappear faster.

