



Regain



OEKO-TEX®
CONFIDENCE IN TEXTILES



FABRAA®
fabrics with a conscience



Regain

This luxurious 100% RPET woven upholstery textile is in our www.wovenbottles.com collection. Regain is piece dyed and fits all types of upholstery.

Woven on an air jet loom with micro-chenille yarns, these yarns provide a voluminous, chunky and comfortable handfeel.

The non-woven backing is made from 100% RPET, which makes Regain a 100% sustainable product. We would also like to mention that Regain is strong, durable and all certifications are available. Regain has been developed in collaboration with Waste2Wear, experts in polyester textiles made from recycled plastic bottles. Also know for their RA3 and Blockchain technology to ensure full transparency.

Machine-washable at 30 degrees Celsius* and available from stock in a wide and trendy colour line.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

Fabraa Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-quality, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

Composition

/ faceside 100%RPET
/ backside 100%RPET
/ chenille flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67



blush 92




cream 02




darkbrown 18



darkgrey 68



eucalyptus 193




hazel 96




honey 202



hunter 156



indigo 90



lightgrey 60




liver 10

Please note: colours may vary according to your screen settings.



natural 01



niagara 158




ocre 23




plumb 168








scarlet 141



taupe 12



zinc 167



Please note: colours may vary according to your screen settings.

Regain - Article passport

A micro chenille sustainable quality with a soft handfeel and a matt and rich look.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100%RPET
Composition backside	100%RPET
Bonding	non-woven
Statistic code	58013300
Dyeing method	piece dyed
Available colours	19
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
dark colours	CTL	grade	4	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/A	
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processingspecifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 40
Material weight in grams per linear meter	± 497

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.603	823	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	101,4	127,2	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	21,3	20,6	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	0,0	n/a	n/a	A/A

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.



FABRAA[®]
fabrics with a conscience

Textafoam b.v.

La Défense 11 | 5026 SC Tilburg

P.O. Box 12 | 5050 AA Goirle

The Netherlands

T +31(0)13 534 5934

F +31(0)13 534 7586

E info@fabraa.com

www.fabraa.com

nov 2021