

RENEGADE



pearl 106




natural 01



desert 109




shell 196



steel 149




liver 10



plumb 168



graphite 66




wood 108



teal 198



indigo 90



forest 162



copper 126



mustard 06



brandy 127



carmine 36


Renegade - Article passport

Fabric with multicoloured aspect, rough construction and soft and full handfeel. Available from stock in a wider range of contemporary and commercial colours.

Product characteristics

Product group	chenille flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Statistic Code	58013600
Coating	SBR
Dyeing method	piecedyed
Available colours	16










Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min. 5	A
	middle colours	CTL	grade	5		min. 4	min. 5	A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
Colour fastness to rubbing	dark colours	CTL	grade	5	5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	Ignitability	 BS5852 part 1 (1979) from The Furniture and Furnishings (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source: cigarette	CTL		passed			

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 714							
Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1,157	1,897	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	140,8	170,5	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,8	2,0	max. 5	max. 4	A/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Dimensional change for washing 30 degrees Celsius/air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	+ 0,0	- 0,4	n/a	n/a	A/A
    		We recommend to immediately place the cover back to the piece of furniture slightly damp after washing.		   				

Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl