

# ROVER



steel 149



niagara 158



silver 125



navy 49



petrol 56



anthracite 67



pine 199



turquoise 44



onyx 169



gold 132



forest 162



army 14



winered 39



scarlet 141



magnolia 160



bordeaux 37



saffron 183



blush 92



coffee 81



pearl 106



linen 110



almond 82

## Rover - Article passport



Rover is woven velvet with a soft and voluminous handfeel and a trendy and luxury look.

Available from stock in a wide range of contemporary and commercial colours.

### Product characteristics

Product group	polyester woven velvet
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Statistic Code	58013700
Coating	milky
Dyeing method	piecedyed
Available colours	21

### Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09	
				DRY	WET	DGM	DGM±		
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	A	
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	5		min. 3-4	min. 4	A	
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5								
	light colours	CTL	grade	5		min. 4	min. 5	B	
	middle colours	CTL	grade	5		min. 4	min. 5	B	
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11								
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A	
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A	
Colour fastness to rubbing	dark colours	CTL	grade	3-4	3	dry: 4, wet: 3	dry: min 4, wet: 3-4	C/B	
	Ignitability (cigarette test)		BS5852 part 1 (1979) from The Furniture and Furnishings (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 0: cigarette		Centexbel	passed			
			DIN EN ISO 1021-1:2014. Source: Smouldering cigarette		Centexbel	passed			
Ignitability (match test)		BS5852 part 1 (1979) from The Furniture and Furnishings (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 1: Match flame equivalent		Centexbel	passed				
		DIN EN ISO 1021-2:2014. Source: Match flame equivalent		Centexbel	passed				

### Processing specifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 40
Material weight in grams per linear meter	± 600

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM±	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.480	1.804	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	49,0	53,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,0	3,0	max. 5	max. 4	A/A
Chemical substances	REACH	Centexbel		passed				

### Cleaning specifications

    	   
---	---



**Textaafoam**  
creativity in fabrics

Textaafoam b.v.  
La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle The Netherlands

T +31(0)13 534 5934  
F +31(0)13 534 7586  
E info@textaafoam.nl  
www.textaafoam.nl