


TUNDRA



navy 49



cobalt 46



niagara 158




mint 50



turtle 88



pesto 194



petrol 56



taupe 12



natural 01



liver 10



wood 108



anthracite 67



steel 149



lightgrey 60



grey 65



blush 92



blackberry 177



scarlet 141



brandy 127



copper 126



rust 29



honey 202

Tundra - Article passport

Flatwoven quality with a light mélange effect.

Available from stock in a wider range of contemporary and commercial colours.

Product characteristics

Product group	polyester Trevira CS flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery, drapery
Composition face side	100% PESTREVIRA CS
Statistic Code	54075200
Dyeing method	piecedyed
Available colours	22

Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2008	CTL	cycles	75.000	>12.000	>12.000	>16.000	A
Pilling	DIN EN ISO 12452-2:2000-11. 2000 cycles	CTL	grade	4-5	min.3-4	min.4		A
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5	min.4	min.5		A
	middle colours	CTL	grade	5	min.4	min.5		A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	4-5	dry:4, wet:3	dry: min 4, wet:3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry:4, wet:3	dry: min 4, wet:3-4	A/A
Ignitability (cigarette test)	DIN EN ISO 1021-1:2014. Source: Smouldering cigarette	Trevira CS			passed			
	BS5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 0: cigarette	Trevira CS			passed			
Ignitability (match test)	DIN EN ISO 1021-2:2014. Source: Match flame equivalent	Trevira CS			passed			
	BS5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 1: Match flame equivalent	Trevira CS			passed			
Ignitability (crib)	DIN EN ISO 1021-2:2014. Source: Match flame equivalent	Trevira CS			passed			
	BS5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 5: Crib 5	Trevira CS			passed			






Processing specifications

Minimum workable width in centimeters	± 141
Roll length in meters	± 50
Material weight in grams per linear meter	± 515







Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.615	650	min.350	min.400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	97,8	63,4	min.25	min.30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	2,0	max.5	max.4	A/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Dimensional change for washing 30 degrees Celsius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,8	0,0	n/a	n/a	A/A

We recommend to immediately place the cover back to the piece of furniture slightly damp after washing.

Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl

