



TECHNICAL SPECIFICATION SHEET

ARTICLE NAME:	SIERRA
RAW MATERIAL:	BOVINE LEATHER - VARIOUS
AVERAGE SIZE:	ca. 4,2 m2
THICKNESS:	ca. 0.9 mm.

Test	Test Method	Result
Colour fastness to rubbing		
Nr. 500 dry rubs	IUF 450/UNI EN ISO 11640	>= 4 grey scale
Nr. 150 wet rubs	IUF 450/UNI EN ISO 11640	>= 4 grey scale
Nr. 80 alkaline pH 8	IUF 450/UNI EN ISO 11640	>= 4 grey scale
Flexing endurance		
	IUP 20 / UNI EN ISO 5402	>= 30.000
Tear strength		
	IUP 40 / UNI EN ISO 3377-I	>= 20 N
Adhesion		
	IUF 470 / UNI EN ISO 11644	>= 3.50 N/cm
Light resistance (xenon test)		
	IUF 402 / UNI EN ISO 105-B02	5 blue scale
Fire resistance		
	UNI EN ISO 1021-1/2	pass
	BS 5852 1991 Sec. 4 NI/0-1	pass
	California T.B. 117	pass

All our leathers comply with the strict regulations and EU Directives covering the use and presence of PCP, CFC, Chromo VI, Dimethylfumarate (DMF) and Azo dyestuffs during the tanning process.
Due to the natural properties of leather colour variations between one dye lot and another may occur.
This technical specification sheet replaces any copies in your possession. The values indicated in this sheet refer to the leather at the time of supply. Once the leather has been processed, cut, marked we can no longer guarantee the same values.

Vicolo Marconi,1 - 36071 Arzignano (VI) - ITALY

Tel. +39 0444 451455 - Telefax +39 0444 451832

e-mail: futura@futuraleathers.com - <http://www.futuraleathers.com>