



CRAFT



graphite 66



zinc 167




lightgrey 60




clay 84




brown 15




espresso 123



dolphin 180



niagara 158



hyacinth 159



coral 95



cinnamon 94



mustard 06



green 55

Craft - Article passport

A multicoloured quality with a woolly look and feel.

Available from stock in a wider range of contemporary and commercial colours.

Product characteristics

Product group	polyester polyacrylic flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	54% PAC 46% PES
Statistic Code	54077300
Coating	needle punch
Dyeing method	yarn dyed
Available colours	13

Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	55.000		min. 12.000	min. 18.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min. 5	A
	middle colours	CTL	grade	5		min. 4	min. 5	A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 0: cigarette	Centexbel		passed				
	DIN EN ISO 1021-1:2014. Source: Smouldering cigarette	Centexbel		passed				
Ignitability (match test)	BS5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part 1. Ignition source 1: Match flame equivalent	Centexbel		passed				
	DIN EN ISO 1021-2:2014. Source: Match flame equivalent	Centexbel		passed				

Processing specifications

Minimum workable width in centimeters	± 142							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 700							
Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.377	1.014	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	204,8	151,8	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,4	2,8	max. 5	max. 4	A/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle The
Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl