



Society





Society

This sustainable bouclé textile has a luxurious look & feel. Our product development team created this fabric together with a weaver who is known for his unique recycled polypropylene.

This textile is made from 100% recycled polypropylene, a special type of polypropylene, coming from leftovers from diapers and masks. Society is multicoloured, soft with a rough and modern look.

Society fits all types of upholstery, so it can be applied widely, as loose covers as well as on tight-fitted furniture.

It is voluminous and has a comfortable handfeel. Society can be machine-washed at 30 degrees Celsius* without losing its characteristics.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

Fabraa Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-quality, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

Composition

/ faceside 100%RPP
/ backside n/a
/ flatweave

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



cinnamon 94



cream 02



denim 153



espresso 123




graphite 66



grey 65



liver 10



mustard 06



natural 01



petrol 56



scarlet 141



shitake 124

Please note: colours may vary according to your screen settings.



steel 149



taupe 12



teal 198



turtle 88



wood 108



Please note: colours may vary according to your screen settings.

Society - Article passport

A sustainable boucle textile with a luxurious look & feel.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

| | |
|----------------------|---|
| Productgroup | flatweave |
| Applications | sofa's, beds, chairs with fitted and loose fitting upholstery |
| Composition faceside | 100%RPP |
| Composition backside | n/a |
| Bonding / Coating | n/a |
| Statistic code | 54077300 |
| Dyeing method | yarn dyed |
| Available colours | 17 |
| Packaging | transparent plastic |

Durability specifications

| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RALGZ430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
|-------------------------------------|---|--|--------|------------|----------------|-------------------------|--------------------|----------------------------|
| | | | | Dry | Wet | DGM | DGM+ | |
| Abrasion resistance - yarn breakage | DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03 | CTL | cycles | 45.000 | | min. 12.000 | min. 16.000 | A |
| Pilling | DIN EN ISO 12945-2:2000-11. 2000 cycles | CTL | grade | 4 | | min. 3-4 | min. 4 | B |
| Colour fastness to light | DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5 | | | | | | | |
| | light colours | CTL | grade | 5 | | min. 4 | min.5 | B |
| | middle colours | CTL | grade | 5 | | min. 4 | min.5 | B |
| Colour fastness to rubbing | DIN EN ISO 105-X12:2016-11 | | | | | | | |
| | light colours | CTL | grade | 5 | 5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A |
| | middle colours | CTL | grade | 5 | 5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A |
| dark colours | CTL | grade | 4-5 | 4-5 | dry: 4, wet: 3 | dry: > 4, wet: 3-4 | A/A | |
| | ignitability (cigarette test) | BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette | CTL | passed | | | | |

Processingspecifications

| Minimum workable width in centimeters | ± 138 | | | | | | | |
|---|--|-------------------------|--------|------------|-------|-------------------------|----------|----------------------------|
| Roll length in meters | ± 40 | | | | | | | |
| Material weight in grams per linear meter | ± 588 | | | | | | | |
| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RALGZ430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
| | | | | Warp | Weft | DGM | DGM+ | |
| Tensile strength | DIN EN ISO 13934-1:2013-08 | CTL | Newton | 903 | 1.375 | min. 350 | min. 400 | A/A |
| Tear growth resistance | DIN EN ISO 13937-3:2000-06 | CTL | Newton | 148,0 | 140,4 | min. 25 | min. 30 | A/A |
| Resistance to seam slippage | DIN EN ISO 13936-2:2004-07. Load 180 N | CTL | mm | 2,2 | 2,2 | max. 5 | max. 4 | A/A |
| Delamination | DIN 53530:1981-02 | CTL | Newton | n/a | n/a | n/a | n/a | n/a |
| Chemical substances | REACH | Centexbel | | passed | | | | |
| | Oeko-Tex, product class II | Centexbel | | certified | | | | |

Cleaning specifications

| Test | Test specification | Executed by laboratory: | Unit | Testresult | | Norm RALGZ430/4:2019-01 | | Norm DIN EN 14 465:2006-09 |
|--|---|-------------------------|------|------------|------|-------------------------|------|----------------------------|
| | | | | Warp | Weft | DGM | DGM+ | |
| Dimensional change for washing 30 degrees celcius / air drying | DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08 | CTL | % | 0,0 | 0,0 | n/a | n/a | A/A |

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.



OEKO-TEX®
CERTIFIED



FABRAA®
fabrics with a conscience

Textafoam b.v.

La Défense 11 | 5026 SC Tilburg

P.O. Box 12 | 5050 AA Goirle

The Netherlands

T +31(0)13 534 5934

F +31(0)13 534 7586

E info@fabraa.com

www.fabraa.com

nov 2021