

DESIGN BY
NORONEN
SINCE 1961



Mito




OEKO-TEX®
CONFIDENCE IN TEXTILES







anthracite 67



ashgrey 40



azure 144



beige 05



blue 45




burgundy 34



cinnamon 94




cognac 28




desert 109



darkgrey 68



dolphin 180




green 55

Please note: colours may vary according to your screen settings.



hunter 156



iceblue 43



liver 10



mustard 06



natural 01




onyx 169




pale 200



pearl 106



slate 87



steel 149

Please note: colours may vary according to your screen settings.

Mito - Article passport


A piece dyed, durable and strong article with a rough structure.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	90%PES 10%NY
Composition backside	100%PES
Bonding	non-woven
Statistic code	54075200
Dyeing method	piece dyed
Available colours	22
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	40.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Colour fastness to rubbing	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL	passed				

Processing specifications

Minimum workable width in centimeters	± 143							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 493							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1,046	496	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	70,3	96,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,7	2,9	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	40,0	31,7	n/a	n/a	n/a
Chemical substances	REACH	Centexbel	passed					
	Oeko-TEX, product class II	Centexbel	certified					

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	-1,2	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
 - Please note that during washing the damp- and dirt prevented treatment will disappear faster.
 - Dirt and damp prevention treatment applied.

