

NORONEN

Ribcord





anthracite 67



aqua 143



army 14



blackberry 177



blossom 166



cacao 83



carmine 36



charcoal 79 (new colour)



chocolate 17



cinnamon 94



cream 02



darkblue 48

Please note: colours may vary according to your screen settings.



desert 109



dolphin 180



emerald 184



espresso 123



gold 132 (new colour)



grey 65



hazel 96



hunter 156



ivory 101



lavender 71



lightgrey 60



magnolia 160

Please note: colours may vary according to your screen settings.



mint 50



mocca 13



natural 01



onyx 169



petrol 56



sand 03



shell 196



taupe 12



thyme 206



turquoise 44



turtle 88



white 104

Please note: colours may vary according to your screen settings.



winered 39

Please note: colours may vary according to your screen settings.

Ribcord - Article passport

A durable, soft, voluminous and elegant corduroy.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	ribcord
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	88%PES 12%PA
Composition backside	100%PES
Bonding	woven
Statistic code	54076130
Dyeing method	piece dyed
Available colours	37
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM DGM+		
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	100.000		min: 20.000min: 40.000		A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min: 3min: 4		A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min: 4min: 5		B
	middle colours	CTL	grade	5		min: 4min: 5		B
	dark colours	CTL	grade	5		min: 4min: 5		B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 140							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 540							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1,432 9/3		min: 350min: 400		A/A
			Newton	96,4 70,4		min: 25min: 30		A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	mm	2,0 1,8		max: 5max: 4		A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	Newton	15,4 33,5		n/a n/a		n/a
Delamination	DIN 53530:1981-02	CTL		passed				n/a
	REACH	Centexbel		certified				
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	laboratory:	Test specification	Executed by	Unit	Testresult	Norm RAL GZ 430/4:2019-01	Norm DIN EN 14 465:2006-09
Dimensional change for washing 30 degrees celsius / air drying	Warp Weft DGM DGM+	DIN EN ISO 5077:2008-04, CTL% 0,80,0n/an/a DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08					A/A
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.							

