

NORONEN



Chic





anthracite 67



onyx 169



white 104



beige 05



lightgrey 60



plumb 168



khaki 51



taupe 12



chocolate 17



caramel 16



petrol 5



navy 49



red 35



cabernet 205



grey 65



olive 53

Chic - Article passport



Strong fabric, suitable for intensive use. Velvet with a cloudy aspect and full and dry grip.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Product group	polyester woven velvet
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Statistic Code	58013700
Coating	transparent
Dyeing method	piecedyed
Available colours	16

Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance- yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min.8.000	min.16.000	A
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	4-5		min.3-4	min.4	A
Colour fastness to light	DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	5		min.4	min.5	A
	middle colours	CTL	grade	5		min.4	min.5	A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry:4, wet:3	dry:min 4, wet:3-4	A/A
	middle colours	CTL	grade	4-5	5	dry:4, wet:3	dry:min 4, wet:3-4	A/A
Ignitability (cigarette test)	BS5852 part 1(1979) from The Furniture and Furnishing (Fire)(Safety) Regulations: 1988 No.1324, Schedule 4 part I, Ignition source 0: cigarette							
		Centexbel		passed				
	DIN EN ISO 1021-1:2014, Source: Smouldering cigarette							
Ignitability (match test)	BS5852 part 1(1979) from The Furniture and Furnishing (Fire)(Safety) Regulations: 1988 No.1324, Schedule 4 part I, Ignition source 1: Match flame equivalent							
		Centexbel		passed				
	DIN EN ISO 1021-2:2014, Source: Match flame equivalent							

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 720							
Test	Test Specification	Executed by laboratory:	Unit	Test result		Norm RALGZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.344	1.208	min.350	min.400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	56,3	170,4	min.25	min.30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180N	CTL	mm	3,0	3,0	max.5	max.4	A/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

