

# Rush





Rush 101



Rush 104



Rush 105



Rush 119



Rush 201



Rush 203



Rush 215



Rush 312



Rush 400



# Rush





Rush-401



Rush-500



Rush-519



Rush-800



Rush-801



Rush-802



Rush-808



Rush-809





- SLIBBROEK 39
  5081 NR HILVARENBEEK
  NETHERLANDS
- +31 13 50 57 555
- +31 13 50 57 554
- WWW.LEOTEX.NL
- O KVK NR: 18023875

## Rush

#### **Product information**



Total composition Composition faceside Composition backing Water repellent finish Useful fabric width Average roll length Fabric weight HS code 100% PES 100% PES 100% PES Yes 140 +/- 2%cms 31m 430 g/m2 6005370000

#### **Important fabric characteristics**

- Upholstery fabrics are sensitive to direct influx of ultraviolet light (sun-or halogen light) and may discolour over time.
- ☐ Intense and dark colours are more sensitive to discoloration caused by ultraviolet light.
- ☐ Intense and dark colours have a lower rub fastness grade.
- $\square$  Wet fabrics have a lower rub fastness grade.
- $\square$  Dye lot differences may occur.
- $\square$  Pilling caused by clotting of upholstery fabric fibres with dust or other fibres may occur.
- ☐ It is recommended to maintain the humidity level of the room to guarantee the elasticity of the fibres and avoid build-up of static electricity.
- $\hfill \Box$  Light and plain fabrics are more sensitive to staining.
- $\square$  Direct contact with chemical solvents (e.g. in glue sprays) can deteriorate fabric properties.
- $_{\square}$   $\,$  In contact with sharp objects scissors, cutters, nails ...) surface damage or pulled loops are unavoidable.
- $\hfill \square$  Do not expose upholstery fabric to direct heat sources.

#### **Fabric care instructions**

















- SLIBBROEK 39
  5081 NR HILVARENBEEK
  NETHERLANDS
- **1** +31 13 50 57 555
- +31 13 50 57 554
- WWW.LEOTEX.NL
- O KVK NR: 18023875



### **Product information**



### **Technical specifications**

Martindale 60000 > 100.000	rubs (pile worn off > 5mm2) rubs (yarn breakage)	EN ISO 12947-2:2016
pilling according to Martindale method		
<u> </u>		EN ISO 12945-2:2000
note 4-5 note 4-5	500 rubs 1.000 rubs	
note 4-5	2.000 rubs	
note 4-5	5.000 rubs	
seam slippage		EN ISO 13936-2:2004
1 mm	warp	
1 mm	weft	
tear strength		EN ISO 13937-3:2000
54 Nabs	warp	
33 Nabs	weft	
tensile strength		EN ISO 13934-1:2013
790 daN	warp	
480 daN	weft	
light fastness		EN ISO 105-B02:2014
note 4-5	dark colours	
note 4-5	light colours	
rub fastness - wet		EN ISO 105-X12:2002
note 4-5	dark colours	
note 4-5	light colours	
rub fastness - dry		EN ISO 105-X12: 2002
note 4-5	dark colours	
note 4-5	light colours	
flame retardancy level		



cigaret

PASS

DIN EN 1021-1:2014