



# Magnum





# Magnum

Magnum is a magnificent addition to our skins collection. The Textafoam Skins Collection includes the best leather alternatives.

Tough and soft, with a matte and vivid natural look. Those are a few key words describing this upholstery fabric Magnum. We are proud to present this commercially strong and promising new item, based on the latest interior fashion trends and years of experience.

Magnum is constructed from 100% virgin polyester woven suede, laminated with a heavy grade fleece backing. Finished and printed in such a way that the look and feel is just like real leather.

We have achieved a solid appearance, also by selecting mainly true to nature colours. Easy to clean and maintain, due to its dirt- and damp prevented treatment so when a stain appears, simply rub gently with a damp cloth.

Kindly note that during daily use, a slightly dull or used aspect will become visible, this has no further influence on the durability of this fabric.

Magnum is also machine-washable at 30 degrees Celsius\*.

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.

**Textafoamoriginals** *Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs everytime. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

## Composition

/ faceside 100%PES  
/ backside 100%PES  
/ microsuede woven

## Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



cabernet 205



chocolate 17



clay 84 (new colour)




cognac 28



graphite 66



jungle 207



lightgrey 60 (new colour)




liver 10



natural 01 (new colour)



onyx 169



plumb 168














stone 181

Please note: colours may vary according to your screen settings.



taupe 12



Please note: colours may vary according to your screen settings.

## Magnum - Article passport


A soft and strong leatherlook with a magnificent dull appearance.

Available from stock in a wide range of contemporary and commercial colours.

### Product characteristics

Productgroup	microsuede woven
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100%PES
Composition backside	100%PES
Bonding	fleece
Statistic code	54075200
Dyeing method	piece dyed
Available colours	13
Packaging	transparent plastic

### Durability specifications






Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	40.000		min. 12.000	min. 18.000	C
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	3-4		min. 3-4	min. 4	B-C
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	3-4		min. 4	min.5	C
	middle colours	CTL	grade	3-4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Colour fastness to rubbing	dark colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	Ignitability (cigarette test)		BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL	passed			

### Processingspecifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 546							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.225	435	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	58,3	29,3	min. 25	min. 30	A/C
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	1,8	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	43,1	33,0	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

### Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RALGZ430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	0,0	n/a	n/a	A/A

- Dirt and damp prevention treatment applied.  
 - We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.  
 - Please note that during washing the damp- and dirt prevented treatment will disappear faster.



**Textaafoam**<sup>®</sup>  
creativity in fabrics

Textaafoam b.v.  
La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle  
The Netherlands

T +31(0)13 534 5934  
F +31(0)13 534 7586  
E info@textaafoam.nl  
www.textaafoam.nl